

KRONOS 2160

Titanium Dioxide

for maximum durability in coatings and plastics

Applications

- White and colored automotive finishes
- Coil coatings
- Powder coatings
- High-quality industrial coatings
- PVC profiles and sidings

Properties

KRONOS 2160 Titanium Dioxide

- Meets the highest demands on outdoor durability
- Imparts high brightness and a neutral tone in white finishes
- Produces clean tones and color stability in colored coatings and plastics
- Delivers good opacity and tinting strength

Product Characteristics

Production	rutile pigment produced by the chloride process
Surface treatment	aluminum and silicon compounds
TiO ₂ content (DIN EN ISO 591)*	≥ 92.0%
Standard classification (DIN EN ISO 591-1)	R 2
ASTM D 476	Type IV & V
Density (DIN EN ISO 787-10)*	3.9 g/cm ³
Bulking value*	0.26 l/kg (0.03 gal/lb)
Oil absorption (DIN EN ISO 787-5)*	19 g/100 g pigment
Color index	Pigment White 6 (77891)
CAS No.	13463-67-7
REACH Registration No.	01-2119489379-17-xxxx

* Typical value

This information pertains solely to the identified product and includes our reliance on testing and information from third parties as of the date hereof. It is not intended to serve as legal, regulatory, or safety advice. It remains the sole responsibility of the customer to determine the suitability of the product when used in specific processes and applications or combined with other materials and to ensure compliance with all relevant laws, regulations, and standards governing those uses. The provision of this information DOES NOT CONSTITUTE A WARRANTY, GUARANTEE, OR REPRESENTATION OF ANY KIND REGARDING PERFORMANCE, SUITABILITY, STABILITY OR OTHERWISE, including compliance with any law, regulation, or industry standard. No contractual obligations or rights, either express or implied, are created between KRONOS and any recipient of this information. © Kronos Worldwide, Inc., KRONOS™ and logo designs associated therewith are copyrights and trademarks of Kronos Worldwide, Inc. and/or its subsidiaries or affiliates.